

IN THE SPECIFICATION:

Please replace the paragraph on page 20, lines 2-6 with the following paragraph:

In particular, the stability is proportionately greater the more the conditions below are respected for the composition:

total true dimer units [[in]] to the isocyanate functions $\leq 30\%$.

Please replace the paragraph on page 39, lines 18-22 with the following paragraph:

1000 g of HDI are heated for 3 hours at 150° in order to carry out a dimerization reaction (5% DC of HDI). A biuret polyisocyanate is synthesized with the mixture obtained, as described in patent application FR 86/12524 (now patent FR 2,603,278) Rhône-Poulenc.